

RECEIVED  
CENTRAL FAX CENTER

DOCKET: CU-2720

JUL 07 2004

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICANT: Hisashi KUGIMOTO )  
SERIAL NO: 10/003,362 )  
FILED: November 15, 2001 )  
TITLE: PROTECTION FILM FOR BASE SHEET )

) Group Art Unit: 1774  
) Examiner: Tamra Dicus

OFFICIAL

THE COMMISSIONER FOR PATENTS  
P.O. Box 1450  
Alexandria, VA 22313-1450

AMENDED CLAIMS

1. (currently amended) A protection film for a base sheet of a lens sheet having a lens surface formed of a UV-curable resin layer, the protection film comprising:  
a resin film; and  
an adhesive formed on one side of said resin film, said adhesive being ~~separable together with~~ allowing said protection film to be releasably separable from said base sheet;  
wherein ~~a transmittance of ultraviolet rays, at least 82% of ultraviolet rays~~ having a wavelength of 320 nm, ~~through~~ are transmitted through the protection film is ~~82% or more.~~
2. (original) A protection film for a base sheet according to claim 1, wherein an adhesive strength is from 0.4 to 2.3 N / 25 mm.
3. (cancelled)
4. (previously presented) A protection film for a base sheet according to claim 1 wherein the adhesive contains a polyolefin-based resin component.
5. (original) A protection film for a base sheet according to claim 1, wherein the material of the base sheet is an acrylic resin.

6. (currently amended) A lens sheet comprising:  
a base sheet; and  
a protection film comprising:  
a resin film; and  
an adhesive formed on one side of said resin film, said adhesive being  
separable together with allowing said protection film at to be release bly  
seperable from said base sheet;  
wherein ~~a transmittance of ultraviolet rays, at least 82% of ultraviolet~~  
rays having a wavelength of 320 nm, ~~through are transmitted through~~ the  
protection film is 82% or more.
7. (currently amended) A lens sheet according to claim 6, wherein ~~the protection~~  
~~film is pasted from the side of the adhesive,~~ a surface of the base sheet has coated  
thereon an antistatic agent containing a cationic surface active agent, and the base  
sheet has a surface resistivity after one year from production of  $10^{12} \Omega / \square$  or less.